

Storage Instructions

- SIBU sheets must always be kept in indoor storage and never outdoors! Moreover, the following instructions are to be followed:
- The sheets should be stored flat. Sheets contained in a roll, should be unpacked and laid out evenly. Weighing down may improve the degree of flatness (warning! Use card as an underlay and weigh down the entire area of the sheet in order to prevent damage).
- The top sheet in a stack should be placed with the upper surface face down.
- SIBU products should be safeguarded against UV-rays.
- SIBU products may not be exposed to moisture or damp.
- SIBU materials should be protected against dirt, dust and mechanical damage.
- Constant temperatures and humidity are to be recommended, approx. +10°C to +30°C and up to 80% humidity. Temperature fluctuations and prolonged storage at temperatures below 0°C or above +30°C can have a negative effect on quality.
- Sheets should not be stored with patterns running in different directions. It is recommended that a layer of card be inserted between the sheets.
- Sheets foreseen for PVA bonding must be used within six months ex-works (SIBU DESIGN Ternberg, please see the date on the sheet label). The reverse side of the pre-treated sheet may neither be dirty, or touched without gloves.

Transport Instructions

- In general, care should be taken that during transport SIBU products are protected against dirt, UV radiation, wetness and mechanical damage.
- Stable, flat pallets should be used with a card underlay. Pallets should be longer than the sheets.
- The uppermost sheet should be placed on the pallet with the upper surface face down.
- The top sheet should also be protected with a sheet of card and a board (e.g. chipboard, HDF, ...).
- The SIBU sheets should be protected against slippage.
- The edges and sides must also be safeguarded (edge protection, PE film, ...).
- Temperatures may not fall below -20°C, or exceed +50°C.
- Sheets should not be transported on pallets with the patterns running in different directions.
- Basically, the transport of SIBU sheets in a rolled condition is possible. The exceptions are LL ROMBO 40, LL ROMBO 85, LL QUADRO, CR CRISTAL, as well as 3D products.
- SIBU products must be acclimatised prior to processing. The correct processing temperature (approx. +15°C to +30°C) must be adhered to.

The enclosed processing instructions must be read prior to use of the sheets. These instructions are also available on the SIBU website.

Sibukle D 22 HV may not be stored at temperatures below +5°C and during transport must be packaged in frost-protective material.

Where possible, SIBU products should be used within 12 months (with the exception of products pretreated with PVA).

For enquiries, please contact your salesperson or retailer.

This information leaflet has been prepared to the best of our knowledge and with special care. Its content derives from practical experience and in-company testing and corresponds with our current know-how. The leaflet should serve as information and does not contain any guarantees with regard to product characteristics or suitability for certain applications. No responsibility is accepted for printing and standard errors and mistakes.